

Artículo/Article	SARGA CANIGO TECNOSANI	MASK FFP2 (test itel CE-11340)
REUSABLE (>25 washes)	MADE IN SPAIN	TESTED (ACCORDING UNE-EN14683 and UNE-EN CEE/93/42)

ANÁLISIS FÍSICO / PHYSICAL ANALYSIS

CARACTERÍSTICAS	RESULTADOS / RESULTS		VALORES / VALUES	TEST	
Nº de Hilo/Thread Count	Urdimbre / Warp	20 1/C			
	Trama / Weft	20 1/C			
Densidad / Density	Urdimbre / Warp	96			
	Trama / Weft	57			
Ligamento / Weave	SARGA 2/1 S / TWILL 2/1 S				
Comp. Urd./ Comp. Warp	35% COTTON / 65% PES			ISO 1833:2006	
Comp. Tr./ Comp.Weft	35% COTTON / 65% PES				
Total Comp.	35% COTTON / 65% PES		Simple: No tolerancia Compuesta: +/- 3%		
Ancho Final / Final Width	cm	160	+/-2%	ISO 3932:1976	
Peso / Weight	gr/m ²	195 - 205	+/-5%	ISO 3801:1977	
Resistencia Rotura/ Breakage	(Kgs.)	Urdimbre	pass	kgf	EN-13795
		Trama	pass	kgf	
Resistencia Abrasion	pass			EN-13795	
Resistencia Desgarro / Tear	Urdimbre/Warp (G)	N/A	Trama / Weft	N/A	EN-13795
Encogimiento / Shrinkage	°C	60	% Urdimbre	+/- 2	0 - 3 %
			% Trama	+/- 2	

SPECIAL MEDICAL TESTS

CARACTERÍSTICAS	RESULTADOS / RESULTS	VALORES / VALUES	TEST
Washing solidity 60°C	5	0-5	UNE EN ISO-05
Pilling	5	0-5	UNE EN ISO 12945-2
Traspirability	< 60 Pa/cm ²		AST1
Aerosol Filtration Efficiency	>94%		UNE EN14683
Particle Filtration Efficiency	>94%		UNE EN14683
Particle Filtration	0,4 micras and >96% efficiency		UNE EN149
Bacterial presence	DRY: PASS WET: PASS		EN-13795

ANÁLISIS QUÍMICO / CHEMICAL ANALYSIS

CARACTERÍSTICAS	RESULTADOS / RESULTS	VALORES / VALUES	TEST
pH	Conforme/According Oeko-Tex II	4,0 - 7,5	UNI EN ISO 3071/06
Formaldehído	Conforme/According Oeko-Tex II	<16ppm <75ppm	UNE EN ISO 14184-1:1999
Arlaminas	Conforme/According Oeko-Tex II	20 ppm	UNE 2002/61/CE

PROHIBIDOS / FORBIDDEN

Metales Pesados	Conforme/According Oeko-Tex II	Niquel 0,5 Pg/cm ² - Cadmio 75 pm - Plomo 100 ppm
AZO Colorants	Conforme/According Oeko-Tex II	No detectable
Colorantes Alérgicos	Conforme/According Oeko-Tex II	No detectable (LMBG) (1/4/96)

SÍMBOLOS DE LAVADO /

WASH CARE SYMBOLS



Observaciones:

TRAS 25 LAVADOS EL ACABADO EMPIEZA A PERDER PROPIEDADES - LAVAR CON DETERGENTE NEUTRO

AFTER 25 WASHES THE FINISH BEGINS TO LOSE PROPERTIES - WASH WITH NEUTRAL DETERGENT

NO USAR LEJIA / DO NOT USE BLEACHING

PLANCHADO A 140° de 10-15 SEGUNDOS / IRON 140° FOR 10-15 SECONDS

GRS POST CONSUME bajo pedido / on request

